



TEST REPORT

Reference No. : WTF22U08158150P
Applicant : ENTTEC Pty Ltd
Address : 43 INDIAN DRIVE, KEYSBOROUGH, VICTORIA 3173, AUSTRALIA
Manufacturer : ENTTEC Pty Ltd
Address : 43 INDIAN DRIVE, KEYSBOROUGH, VICTORIA 3173, AUSTRALIA
Product Name : SmartPXL100x25 dot
Model No. : 73030 – Flat Clear – 1dot – RGB – 24V
Qty. : 1 pcs
Test Environment : 25°C ± 5°C, (50% ± 10%) RH
Standards : ASTM G154-06
Test Category : Commissioned Test
Test Item : UV aging test
Date of Receipt sample : 2022-08-08
Date of Test : 2022-08-08 to 2022-08-16
Date of Issue : 2022-09-13
Test Result : Pass

Remarks:

The report shall not be partially copied without the written approval of the company, and the inspection and test results are only responsible for the test samples.

The report is invalid if it is altered, added or deleted, without the signature of the approver, or without the special seal of our company for inspection and testing.

If the report is not stamped with the certification mark, it is only used for scientific research, teaching, internal quality control and other activities, and cannot be used for the purpose of issuing proof data to the society.

Prepared By:

Waltek Testing Group (Suzhou) Co., Ltd.

Address: NO.4499,Wuzhong Avenue,Hengjing Street,Wuzhong Economic Development Zone,

Suzhou,Jiang Su,China.

Tel : + 86 - 512 - 6655 2666

Fax: + 86 - 512 - 6603 2668

Email: suz@waltek.com.cn

Compiled by:

Mia Xu

Mia xu

Approved by:

Jason Lang

Jason lang



List of test items:

| No. | Test Items | Test Requirement | Model No. | Result |
|-----|---------------|--|---------------------------------------|--------|
| 1 | UV aging test | According to test standard ASTM G154-06 and customer test requirements | 73030 – Flat Clear – 1dot – RGB – 24V | Pass |

Subcontracting:

Whether there is subcontracting to other laboratories:

☐ Yes☒ No

If any ,describe the subcontracted projects and information in detail:

Test items: --

Subcontracted laboratory information: --

Subcontract Report Number: --

Note :N/A

WALTEK



UV aging test

1. Test standard:

According to the standard ASTM G154-06 and customer commissioned testing requirements.

2. Test Method:

Test time:168h;

Irradiance:0.89W•m⁻²•nm⁻¹;

Test condition: 8hours of light,4hours of condensation,light temperature (60°C±3°C),condensing temperature(50°C±3°C).


3. Acceptance Conditions:

After the test, normal function.

4. Test Result:

After the test, normal function.

Appendix I Sample photos before test:



Before the test

Appendix II Test Photo:



Set up



During the test

Appendix III Sample photos after test:

Waltek Testing Group (Suzhou) Co., Ltd.
<http://www.waltek.com.cn>



Function after the test

Appendix IV Equipment Used during Test:

| Equipment | Model/Type | Cal. Due Date |
|--------------------------------------|----------------|---------------|
| Ultraviolet light aging test chamber | WTUP1068A1-001 | 2023-07-08 |

===== End of Report =====

WALTEK